

Technical Data Sheet

Date of Issue 06/06/2016

Rev. 00_06/06/2016

12B

High Duty Rubber PET Tape

**Product Description**

Thicker version of 11B, it has higher dielectric properties, is designed for a range of electrical applications and used for wiring and coil insulation tasks.

It is suitable for sealing inner coil and final wrapping of cast resin capacitors, insulation in motor and coil transformer manufacturing industries and for multi-purpose circuit assembly and repair.

Features

- Meets Class B Electrical Requirements
- Good Ageing Characteristics
- Thermosetting Adhesive
- UL Approved
- Excellent Dielectric Strength

Main Applications

- Coil Insulation
- Motor Insulation
- For use in Manufacture of Small Transformers
- Circuit Assembly and Repairing

Technical Data

	Units	Std. Values
Total Thickness	µm	90
Backing Thickness	µm	50
MD tensile strength	N/cm	70
MD elongation at break	%	90
Peel Adhesion	N/cm	5
Service Temperature (up to)	°C	130
Dielectric Strength	kV	9
Class		B

Backing material

Polyester

Type of adhesive

Thermosetting Rubber

Available colour

Yellow Transparent

Technical Information and Product Use

All technical information and data above mentioned are provided to the best of our knowledge on the basis of our practical experience. Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. The accuracy or completeness of such information is not guaranteed. The technical information, suggestions and other statements contained in this document have been compiled for your guidance and usage. PPM Industries reminds the user of the products to make sure that the product is used as per the instructions and suggestions provided. It is the user's sole responsibility to determine the suitability of the product in actual application under specific conditions.

Storage and Shelf Life

Suggested storage in dry area away from direct sunlight temperature should range from 59°F / 15°C to 77°F / 25°C with max relative humidity of 50%. Tape and jumbo roll should be used respectively within 12 months and 6 months from date of manufacture. PPM Industries does not take responsibility for the defective material if is not stored and used in accordance with the conditions listed above.