



2518LN

Low Noise Acrylic Polypropylene Packaging Tape

Tape Structure

Backing BOPP

Adhesive ACRYLIC EMULSION

2518LN

Description

2518LN is a **Low Noise** polypropylene packaging tape with a low noise adhesive. It has a **quiet unwind** which means reduced noise which is ideal for busy or confined packing lines where noise needs to be reduced.

It has a 25 micron backing thickness which makes it ideal for **medium duty applications**. It has a water based adhesive which works well with both **low** and **high temperatures**.

CHARACTERISTICS	UNITS	STD. VALUES
Total Thickness	mic	43
Backing Thickness	mic	25
MD elongation at break	%	100
Peel Adhesion	gm/cm	>210
Rolling Ball	cm	<8
Shear Strength STD	h	>2

Available colours: BROWN, CLEAR

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions.

DATE OF ISSUE: 06/06/16



IN TAPE WE TRUST




2518LN

Low Noise Acrylic Polypropylene Packaging Tape

Application fields



Skills



Terms & Conditions of liability

PPM tapes must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 15 to 25°C with max. relative humidity of 60%.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust.

It is suggested not to apply the tape with temperatures lower than 10°C.

With a storage temperature lower than 10°C, it is always suggested temperature reconditioning of the tape at room temperature (15°C - 25 °C) before its use.

Shelf life from date of manufacture:

(no yellowing and < 10% loss in performance at 23 °C, 50 % humidity) is considered 12 months for Slit rolls and 6 for Jumbo rolls.

PPM does not take responsibility for the defective material is not stored and used in accordance with the conditions listed above.

Follow us on:



www.ppmindustries.com - www.ppmindustries.co.uk