



25S

Solvent Acrylic Polypropylene Packaging Tape

Tape Structure

Backing BOPP

Adhesive SOLVENT ACRYLIC

25S

Characteristics

25S is a **premium** BOPP packaging tape with a solvent adhesive. With a 25 micron backing it offers **high strength**.

The aggressive adhesive system makes it ideal for **polythene packaging, bundling, and sealing**, it has the ability to perform with **low** and **high temperatures** so it is the ideal choice when the product is to go into a **freezer**.

CHARACTERISTICS	UNITS	STD. VALUES
Total Thickness (no liner)	mic	45
Backing Thickness	mic	25
MD elongation at break	%	100
Peel Adhesion	gm/cm	300
Rolling Ball	cm	<6
Shear Strenght STD	h	>4h

Available colours: BROWN, CLEAR

Figures shown refer to average values only, based on tests carried out in conditioned laboratory and are not valid for specification. The company reserves the right to modify or change the products at any time without notice. All information has to be intended as generic advise for the use of products. Users have to verify the suitability of each tape in actual application under specific conditions.

DATE OF ISSUE: 06/06/16



25S

Solvent Acrylic Polypropylene Packaging Tape

Application fields



Technical features



Terms & Conditions of liability

PPM tapes must be stored in a dry location, protected from direct sunlight exposure and from freezing. Storage temperatures should be as close as possible to room temperature; suggested storage temperature should range from 15 to 25°C with max. relative humidity of 60%.

Make sure the surface you wish to place the tape on is cleaned, dried and free from oil and dust.

It is suggested not to apply the tape with temperatures lower than 10°C.

With a storage temperature lower than 10°C, it is always suggested temperature reconditioning of the tape at room temperature (15°C - 25 °C) before its use.

Shelf life from date of manufacture:

(no yellowing and < 10% loss in performance at 23 °C, 50 % humidity) is considered 12 months for Slit rolls and 6 for Jumbo rolls.

PPM does not take responsibility for the defective material is not stored and used in accordance with the conditions listed above.

Follow us on:



www.ppmindustries.com - www.ppmindustries.co.uk